



# RFB LATEX LIMITED

## Specifications For

### Latex Household Gloves –Flocklined (Avg.Wt (M) 45 gms)

#### PHYSICAL DIMENSIONS

Size	Minimum Length in mm	Width in mm	Minimum Thickness in mm		
			Cuff	Palm	Finger
Small	300	105 ± 5	0.20	0.25	0.30
Medium	300	115 ± 5	0.20	0.25	0.30
Large	300	125 ± 5	0.20	0.25	0.30
X Large	300	135 ± 5	0.20	0.25	0.30

#### PHYSICAL REQUIREMENTS

Properties	Before Aging	After Aging
Tensile Strength in Mpa	10 Mpa	7 Mpa
Ultimate Elongation, minimum	500%	375 %

#### TEST RESULTS

Property	Test Method	Result
Resistance against penetration	EN 374-2	Complies with an AQL of 1.5 at general inspection level - 1
Resistance against permeation	EN 374-2	
<i>Methanol</i>	EN374- 3	<i>Performance Level - 6</i>
<i>NaOH 40%</i>		<i>Performance Level - 2</i>
<i>H<sub>2</sub>SO<sub>4</sub> 96%</i>		<i>Performance Level – 2</i>
Abrasion , Blade Cut ,Tear, Puncture Resistance	EN388	Level 0010
General Requirements/design	EN 420	Complies
Sizes / measures	EN 420	Complies
Dexterity / handling	EN 420	Class – 5

Design	Hand Specific, Curved fingers, textured finish with embossed pattern on the finger and palm surface (front side only).
Cuff	Beaded.
Colour	Yellow with white Flocklined base inside.
Quality Assurance	Manufactured under Good Manufacturing Practice (GMP) and ISO 9001 Quality Systems..



# RFB LATEX LIMITED

## Specifications For

### Latex Household Gloves – Flocklined (Avg.Wt (M) 52 gms)

#### PHYSICAL DIMENSIONS

Size	Minimum Length in mm	Width in mm	Minimum Thickness in mm		
			Cuff	Palm	Finger
Small	300	105 ± 5	0.25	0.30	0.35
Medium	300	115 ± 5	0.25	0.30	0.35
Large	300	125 ± 5	0.25	0.30	0.35
X Large	300	135 ± 5	0.25	0.30	0.35

#### PHYSICAL REQUIREMENTS

Properties	Before Aging	After Aging
Tensile Strength in Mpa	10 Mpa	7 Mpa
Ultimate Elongation, minimum	500%	375 %

#### TEST RESULTS

Property	Test Method	Result
Resistance against penetration	EN 374-2	Complies with an AQL of 1.5 at general inspection level - 1
Resistance against permeation	EN 374-2	
<i>Methanol</i>	EN374- 3	<i>Performance Level - 6</i>
<i>NaOH 40%</i>		<i>Performance Level - 2</i>
<i>H<sub>2</sub>SO<sub>4</sub> 96%</i>		<i>Performance Level - 2</i>
Abrasion , Blade Cut ,Tear, Puncture Resistance	EN388	Level 0010
General Requirements/design	EN 420	Complies
Sizes / measures	EN 420	Complies
Dexterity / handling	EN 420	Class – 5

Design	Hand Specific, Curved fingers, textured finish with embossed pattern on the finger and palm surface (front side only).
Cuff	Beaded.
Colour	Yellow with white Flocklined base inside.
Quality Assurance	Manufactured under Good Manufacturing Practice (GMP) and ISO 9001 Quality Systems..



# RFB LATEX LIMITED

## Specifications For

### Latex Household Gloves – Flocklined (Avg.Wt (M) 60 gms)

#### PHYSICAL DIMENSIONS

Size	Minimum Length in mm	Width in mm	Minimum Thickness in mm		
			Cuff	Palm	Finger
Small	300	105 ± 5	0.30	0.35	0.38
Medium	300	115 ± 5	0.30	0.35	0.38
Large	300	125 ± 5	0.30	0.35	0.38
X Large	300	135 ± 5	0.30	0.35	0.38

#### PHYSICAL REQUIREMENTS

Properties	Before Aging	After Aging
Tensile Strength in Mpa	10 Mpa	7 Mpa
Ultimate Elongation, minimum	500%	375 %

#### TEST RESULTS

Property	Test Method	Result
Resistance against penetration	EN 374-2	Complies with an AQL of 1.5 at general inspection level - 1
Resistance against permeation	EN 374-2	
<i>Methanol</i>	EN374- 3	<i>Performance Level - 6</i>
<i>NaOH 40%</i>		<i>Performance Level - 2</i>
<i>H<sub>2</sub>SO<sub>4</sub> 96%</i>		<i>Performance Level - 2</i>
Abrasion , Blade Cut ,Tear, Puncture Resistance	EN388	Level 0010
General Requirements/design	EN 420	Complies
Sizes / measures	EN 420	Complies
Dexterity / handling	EN 420	Class – 5

Design	Hand Specific, Curved fingers, textured finish with embossed pattern on the finger and palm surface (front side only).
Cuff	Beaded.
Colour	Yellow with white Flocklined base inside.
Quality Assurance	Manufactured under Good Manufacturing Practice (GMP) and ISO 9001 Quality Systems..